



Desmopan 786 L

/

Extrusion- and injection molding grade; high mechanical strength; very good hydrolysis and microbial resistance; good low-temperature flexibility; Application; Film hoses; Fire hoses; Profiles; Technical parts

ISO Shortname

Property	Test Condition	Unit	Standard	Value		
				drying	annealed	-
				according to specifications		
Mechanical properties (23 °C/50 % r. h.)						
C shore hardness, method A		-	ISO 868		85	
C shore hardness, method D		-	ISO 868		34	
Ultimate tensile strength	200 mm/min	MPa	DIN 53504		35,0	
Strain at break	200 mm/min	%	DIN 53504		569	
Stress at 10 % strain	200 mm/min	MPa	DIN 53504		1,8	
Stress at 50 % strain	200 mm/min	MPa	DIN 53504		4,7	
Stress at 100 % strain	200 mm/min	MPa	DIN 53504		6,4	
Stress at 300 % strain	200 mm/min	MPa	DIN 53504		12,7	
C Compression set	24 h; 70 °C	%	ISO 815		50	
C Compression set	72 h; 23 °C	%	ISO 815		18	
C Abrasion resistance		mm³	ISO 4649		39	
Impact resilience		%	ISO 4662		36	
Tear propagation resistance	500 mm/min	kN/m	ISO 34-1		60,2	
Thermal properties						
Tensile storage modulus	-20 °C	MPa	ISO 6721-1,-4		393	
Tensile storage modulus	20 °C	MPa	ISO 6721-1,-4		31	
Tensile storage modulus	60 °C	MPa	ISO 6721-1,-4		18	
Other properties (23 °C)						
C Density		kg/m³	ISO 1183-1			1150
Molding conditions						
Injection molding-Melt temperature		°C	-	210 - 230		
Injection molding-Mold temperature		°C	-			20 - 40
Extrusion-Melt temperature		°C	-	190 - 220		

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Impact properties: N = non-break, P = partial break, C = complete break



Desmopan 786 L

Disclaimer

Disclaimer for Sales products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Test values

Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Please note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mold/die, the processing conditions and coloring.

Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded.

Publisher: Global Innovations - Polycarbonates

Bayer MaterialScience AG,

D-51368 Leverkusen,

www.bayermaterialscience.com